



MATERIAL DATA SHEET

Grade PCGP-HT

Phone
(713) 673-7272
(800) 847-6056

Fax
(713) 673-7218

2075 N. Wayside
P.O. Box 15194
Houston, Texas 77220

- Description:** Port City Grade PCGP-HT is a heat-resistant laminate made from a fiberglass cloth saturated with a high-temperature phenolic resin. PCGP-HT has a high mechanical strength, excellent heat resistance, and low thermal expansion.
- Application:** Motor slot insulation, high temperature electromechanical applications.
- Color:** Black
- Thickness Range:** 0.013" - 2.000"
- Size:** Fabricated parts available in lengths to 48".

Engineering Data

Property	Test Condition	Units	Typical Value
Density	A	gms/cc	1.88
Specific Volume	A	cu in/lb	20.5
Flexural Strength	A		
Lengthwise		psi	61,500
Crosswise		psi	59,000
Flexural Strength	E-1/150		
Lengthwise		psi	50,000
Impact Strength	A	ft-lb/in notch	
Izod, Edgewise			
Lengthwise			20
Crosswise			15
Compressive Strength	A	psi	60,000
Rockwell Hardness	A	M scale	110
Bond Strength (1/2")	A	lb	1,800
Dielectric Strength (Parallel)	A	kv	55
Dielectric Constant	A		6.35
Dissipation Factor	A	@ 1 MHz	.022
Arc Resistance		sec	100
Thermal Expansion		/°F	5 E-5
Water Absorption	D-24/23	percent	
.062			0.28
.125			0.15
Heat Resistance			
Short Term		°F	600
Continuous		°F	450

Values shown are for test samples made from production materials and are believed to be representative. THERE IS NO WARRANTY, EXPRESSED, OR IMPLIED. The purchaser/end user assumes all responsibility for testing and determining the suitability of any material for its intended use.